

## SP 201 COLD FIXING AGENT – WB

### TECHNICAL DATA SHEET

#### USING FIELDS and PROPERTIES

It is an additive used to improve the dry-wet rubbing and washing fastness properties of water based printing pastes in textile printing.  
Especially, it should be added to SP 237 Flock Adhesive - WB in order to get better washing fastness.  
Suitable to ecological standards.

#### PHYSICAL-CHEMICAL PROPERTIES

**Appearance** : Yellowish liquid  
**pH** : 8-9,5 (25 °C/ 77 °F)  
**Density** : 1,08 g/ cm<sup>3</sup> (25 °C/ 77 °F)  
**Viscosity** : [(25 °C) sp: 1, rpm: 20 Brookfield ] : 250 – 350 [mPa.s]

#### APPLICATION

**Mixture** : SP 201 Cold Fixing Agent - WB is used (2-3 %) in water based printing pastes.  
The mixture should be consumed within 24 hours after SP 201 Cold Fixing Agent - WB is added into the water based printing pastes. Otherwise, it can damage the mixture.

#### SAFETY and STORAGE

Printing should be done in ventilated places not to have inhalation problems. In order to prevent contact with hands and eyes, protective glasses and gloves should be used. If it is swallowed, seek for medical assistance.

Keep containers dry and tightly closed. Store in a ventilated place between (+5)-(+30) °C/41-86 F of temperature.

It should be consumed within 12 months after the production date.

#### PACKING

In 1 kg or 0,25 gal of plastic packings.

The technical application and information that have been given above, are designed only as using instructions. Should not be considered as a warranty for any other use. When any help or assistance is required, our technical department is ready for help.